

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Braeside Mills Operations P/L, T/A as Armstrong Flooring
29-39 Mills Road
Braeside VIC 3195

Test Number : 24-004606
Issue Date : 27/11/2024
Print Date : 27/11/2024
Order Number : 208680

Sample Description Clients Ref : "Armstrong Carpet Tile Pile Height 4mm Pile weight 450g/m2 1/10 Gauge PE(H)"
Loop pile carpet tile
End Use : Flooring
Nominal Composition : Solution Dyed Nylon with Polyethylene Backing
Nominal Mass per Unit Area/Density : 450g/m2
Nominal Thickness : Pile: 4mm



337031

74099

Page 1 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved




Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.




Chris Campbell
APPROVED SIGNATORY


MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Braeside Mills Operations P/L, T/A as Armstrong Flooring
29-39 Mills Road
Braeside VIC 3195

Test Number : 24-004606
Issue Date : 27/11/2024
Print Date : 27/11/2024
Order Number : 208680

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 15-11-2024

Date Tested 27-11-2024

CHF Value	1	2	3	Mean
Length	6.6	6.6	6.8	6.7 kW/m ²
Width	7.0	-	-	- kW/m ²
HF-30 Value	1	2	3	Mean
Length	6.6	6.8	-	- kW/m ²
Smoke Value	1	2	3	Mean
Length	71	74	37	61 %.min
Width	54	-	-	- %.min

337031

74099

Page 2 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Braeside Mills Operations P/L, T/A as Armstrong Flooring
29-39 Mills Road
Braeside VIC 3195

Test Number : 24-004606
Issue Date : 27/11/2024
Print Date : 27/11/2024
Order Number : 208680

Observations:

Melting

Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of $23\pm 2^{\circ}\text{C}$ and relative humidity of $50\pm 5\%$ for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

337031

74099

Page 3 of 3

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Chris Campbell

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR