

Latvijas Finieris AS Bauskas iela 59 1004 Riga Latvia

## Test Report No. 55413-001 II

Test objective: Evaluation according to French VOC- and CMR-regulation

Name of test sample/item by client: | Birch plywood Riga Ply BB/WG EXT-LN 18 mm

Sample/batch by client: S-135571 am.2

Sampled by: Dina Melgalve, Latvijas Finieris AS

Date of sampling: 23.07.2020

Location of sampling: mill Lignums, Finiera iela 6 Riga LV-1016

Date of production: 23.07.2020

Date of arrival of sample: 30.07.2020

Test period: 30.07.2020 - 13.10.2020

Date of report: 14.10.2020

Number of pages of report: 16

Testing laboratory: eco-INSTITUT Germany GmbH, Cologne

except ‡ subcontracted # outside accreditation

Test objective fulfilled: 

✓ Class A+

Note:

The test results in the report refer exclusively to the test sample submitted by the manufacturer. The report is not permitted to be used in product and company advertising. The report may be published in full as technical documentation on the Internet with the written consent of eco-INSTITUT Germany GmbH. eco-INSTITUT Germany GmbH has recommended that the manufacturer repeats the test after 3 years at the latest. More information at

www.eco-institut.de/en/advertising

Nach DIII EN 190/IEC 17825 akkredmentes Aruffabo

DAKS

Deutsche
Akkrediterung sstelle
D-PL-20051-01-00



## Content

Sample View	
Statement of conformity with VOC- and CMR- regulation	
Summary statement of conformity	
Déclaration de conformité avec les critères du COV décret et du CMR arrêté	
Résumé de la déclaration de conformité	
Laboratory report	
1 Emission analysis	8
1.1 Sample A001, Volatile Organic Compounds after 28 days	
Phthalates, chamber air analytics	
Appendix	
Sampling sheet	
Definition of terms	13
Commentary on emission analysis	15
Explanation of Specific Emission Rate SER	



# Sample View

Internal sample-no. (will be filled in by laboratory)	Test sample/item by client	Sample/batch by client:	Condition upon delivery	Type of sample
A001	Birch plywood Riga Ply BB/WG EXT-LN 18 mm	S-135571 am.2	without objection	flooring



A001: Birch plywood Riga Ply BB/WG EXT-LN 18 mm



## Statement of conformity with VOC- and CMR- regulation

The product Birch plywood Riga Ply BB/WG EXT-LN 18 mm has been tested on behalf of Latvijas Finieris AS.

This evaluation bases on the test criteria of the decree no. 2011-321 of March 23<sup>rd</sup>, 2011 (VOC regulation) and executive decisions of May 28th, 2009 and April 30th, 2009 (CMR regulation) of the French Ministry of Ecology, Sustainable Development, Transport and Housing.

The results documented in the test report were evaluated as follows.1

### **VOC** regulation

Emission analysis	Concentration (Test chamber air) [µg/m³]	Class			
Substance	after 28 days	С	В	Α	A+
Formaldehyde	2	> 120	< 120	< 60	< 10
Acetaldehyde	9	> 400	< 400	< 300	< 200
Toluene	< 1	> 600	< 600	< 450	< 300
Tetrachlorethylene	< 1	> 500	< 500	< 350	< 250
Xylene	< 1	> 400	< 400	< 300	< 200
1,2,4-Trimethylbenzene	< 1	> 2000	< 2000	< 1500	< 1000
1,4-Dichlorbenzene	< 1	> 120	< 120	< 90	< 60
Ethylbenzene	< 1	> 1500	< 1500	< 1000	< 750
2-Butoxyethanol	< 1	> 2000	< 2000	< 1500	< 1000
Styrene	< 1	> 500	< 500	< 350	< 250
TVOC <sub>tol</sub>	51	> 2000	< 2000	< 1500	< 1000

### CMR regulation

Concentration (Test Requirement **Emission analysis** chamber air) [µg/m³] [µg/m³] Substance after 28 days after 28 days Benzene < 1 < 1 Trichlorethylene < 1 < 1 Di(2-ethylhexyl)phthalate (DEHP) < 1 < 1 Dibutylphthalate (DBP) 1 < 1

¹ If a measurement result that slightly exceeds the specification is assessed as "not fulfilled", this is based on the agreement of the "shared risk of measurement uncertainty (shared risk approach)". According to this, the probability that the statement is correct is  $\geq$  50%. Similarly, a result slightly below the specification value also only has a probability of  $\geq$  50% of being compliant. I.e., the risk of making a false negative statement regarding the fulfilment of the specification is just as high as the risk of making a false positive statement (more information at <a href="https://www.eco-institut.de/en/2019/07/measurement\_uncertainty/">https://www.eco-institut.de/en/2019/07/measurement\_uncertainty/</a>).



## Summary statement of conformity

The product **Birch plywood Riga Ply BB/WG EXT-LN 18 mm** meets the requirements of the **Class A+** of the decree no. 2011-321 of March 23, 2011 (VOC regulation) and executive decisions of May 28<sup>th</sup>, 2009 and April 30<sup>th</sup>, 2009 (CMR regulation) of the French Ministry of Ecology, Sustainable Development, Transport and Housing.

Cologne, 14.10.2020

Arne Herzog

(Project Manager)

<u>Remark</u>: It is not permitted to publish extracts of this report and the comments on the first page of this report apply.



### Déclaration de conformité avec les critères du COV décret et du CMR arrêté

Le produit **Birch plywood Riga Ply BB/WG EXT-LN 18 mm** a été testé sous la responsabilité du **Latvijas Finieris AS**. Cette évaluation est basée sur les critères du décret n° 2011-321 du 23 mars 2011 (COV décret) et arrêté du 28 mai 2009 et 30 avril 2009 (CMR arrêté) par le Ministère de l'écologie, du développement durable, des transports et du logement.

Les résultats documentés dans le rapport du test sont évalués comme suit.<sup>2</sup>

#### COV décret

Analyse des émissions	Concentration (air de la chambre d'essai) [µg/m³]		Classe		
Substance	au bout de 28 jours	С	В	A	A+
Formaldéhyde	2	> 120	< 120	< 60	< 10
Acétaldéhyde	9	> 400	< 400	< 300	< 200
Toluène	< 1	> 600	< 600	< 450	< 300
Tétrachloréthylène	< 1	> 500	< 500	< 350	< 250
Xylène	< 1	> 400	< 400	< 300	< 200
1,2,4-Triméthylbenzène	< 1	> 2000	< 2000	< 1500	< 1000
1,4-Dichlorobenzène	< 1	> 120	< 120	< 90	< 60
Ethylbenzène	< 1	> 1500	< 1500	< 1000	< 750
2-Butoxyéthanol	< 1	> 2000	< 2000	< 1500	< 1000
Styrène	< 1	> 500	< 500	< 350	< 250
COVT <sub>tol</sub>	51	> 2000	< 2000	< 1500	< 1000

#### CMR arrêté

Analyse des émissions	Concentration (air de la chambre d'essai) [µg/m³]	Valeur limite [µg/m³]
Substance	au bout de 28 jours	au bout de 28 jours
Benzène	< 1	< 1
Trichloréthylène	< 1	< 1
Phthalate de bis (2-éthylhexle) (DEHP)	< 1	< 1
Phthalat de dibutyle (DBP)	< 1	<1

<sup>&</sup>lt;sup>2</sup> Si un résultat de mesure dépasse légèrement les exigences et est évalué "non conforme", cette évaluation se base sur l'accord du "risque partagé d'incertitude de mesure (Shared Risk-Ansatz)". La probabilité que la déclaration soit correcte est ensuite ≥ 50 % De même, un résultat légèrement inférieur à la valeur requise n'est conforme qu'avec une probabilité de ≥ 50%. Cela signifie que le risque de faire une fausse déclaration négative pour satisfaire à l'exigence est aussi élevé que le risque de faire une fausse déclaration positive (plus d'informations sur <a href="https://www.eco-institut.de/en/2019/07/measurement\_uncertainty/">https://www.eco-institut.de/en/2019/07/measurement\_uncertainty/</a>).



## Résumé de la déclaration de conformité

Le produit **Birch plywood Riga Ply BB/WG EXT-LN 18 mm** correspond aux exigences de la **classification A+** sur les critères du décret n° 2011-321 du 23 mars 2011 (COV décret) et arrêté du 28 mai 2009 et 30 avril 2009 (CMR arrêté) par le Ministère de l'écologie, du développement durable, des transports et du logement.

Cologne, 14.10.2020

Arne Herzog (chef de projet)



## Laboratory report

#### 1 Emission analysis

#### Test method

DIN EN 16516:2018-01 Testing and evaluation of the release of dangerous substances;

determination of emissions into indoor air

A001, Preparation of test sample

Date: 09.09.2020
Sample preparation: not applicable

Masking of backside: yes Masking of edges: yes,

Relationship of unmasked not applicable

edges to surface:

Loading: related to area Dimensions: 25 cm x 20 cm

#### A001, Test chamber conditions according to DIN ISO 16000-9:2008-04

Chamber volume: $0.125 \text{ m}^3$ Temperature: $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ Relative humidity: $50 \% \pm 1 \%$ Air pressure:normalAir:cleanedAir change rate: $0.5 \text{ h}^{-1}$ Air velocity:0.3 m/s

Loading: 0.4 m/m<sup>3</sup> Specific air flow rate: 1.25 m $^{3}$ (m $^{2} \cdot$  h)

Air sampling: 28 days after test chamber loading

#### Analytics

Aldehydes and Ketones DIN ISO 16000-3:2013-01

Limit of determination: 2 µg/m³

Volatile Organic Compounds DIN ISO 16000-6:2012-11

Limit of determination: 1 μg/m³ (1,4-Cyclohexanedimethanol, Diethylene glycol,

1,4-Butanediol: 5 µg/m³)

Note for analysis: not specified



## 1.1 Sample A001, Volatile Organic Compounds after 28 days

#### Test objective:

Volatile Organic Compounds according to "Arrêté du 19 avril 2011 relatif à l'étiquetage des produits de construction ou de revêtement de mur ou de sol et des peintures et vernis sur leurs émissions de polluants volatils" (french VOC-regulation, 10 substances) and "Arrêté du 30 avril 2009 relatif aux conditions de mise sur le marché des produits de construction et de décoration contenant des substances cancérigènes, mutagènes ou reprotoxiques de catégorie 1 ou 2" (french CMR-regulation, 2 substances), test chamber, air sampling 28 days after test chamber loading

#### Test result:

Sample:

A001: Birch plywood Riga Ply BB/WG EXT-LN 18 mm

No.	Substance	CAS No.	RT	Concentration+ (test chamber air)	Toluene- equivalent
				Substances ≥ 1 µg/m³ 28 days	Substances ≥ 5 µg/m³ 28 days
			[min]	[µg/m³]	[µg/m³]
1	Aromatic hydrocarbons				
1-1	Toluene	108-88-3		< 1	< 5
1-2	Ethyl benzene	100-41-4		< 1	< 5
1-3	Xylene, mix of o-, m- and p-xylene isomers	1330-20-7		< 1	< 5
1-4	p-Xylene (including m-Xylol)	106-42-3		< 1	< 5
1-6	o-Xylene	95-47-6		< 1	< 5
1-11	1.2.4-Trimethylbenzene	95-63-6		< 1	< 5
1-25	Styrene	100-42-5		< 1	< 5
6	Glycols, Glycol ethers, Glycol esters				
6-3	Ethylene glycol-monobutylether (2- Butoxyethanol)	111-76-2		< 1	< 5
7	Aldehyde				
7-20	Acetaldehyde	75-07-0		9	n.d.
7-22	Formaldehyde	50-00-0		2	n.d.



No.	Substance	CAS No.	RT	Concentration+ (test chamber air)	Toluene- equivalent
				Substances ≥ 1 µg/m³ 28 days	Substances ≥ 5 µg/m³ 28 days
			[min]	[µg/m³]	[µg/m³]
13	Other identified substances in addition to LCI list				
	Benzene	71-43-2		< 1	< 5
	1,4-Dichlorobenzene	106-46-7		< 1	< 5
	Trichlorethene	79-01-6		< 1	< 5
	Tetrachloroethene	127-18-4		< 1	< 5

 $<sup>\</sup>mbox{+}\mbox{ identified}$  and calibrated substances, substance specific calculated

n.d. = not determinable

TVOC, Total volatile organic compounds	Concentration after 28 days [µg/m³]	SERa [µg/(m² • h)]
Sum of VOC according to ISO 16000-6	51	64



## 2 Phthalates, chamber air analytics

#### Test parameter:

Phthalates, test chamber, air sampling 28 days after test chamber loading

#### Test method:

Analytics: DIN ISO 16000-6:2012-11

#### Test result:

Sample	Substance	Concentration (test chamber air) [µg/m³]	Limit of determination (test chamber air) [µg/m³]
A001: Birch plywood Riga	Dibutylphthalate (DBP)	< q.l.	1
Ply BB/WG EXT-LN 18 mm	Diethylhexylphthalate (DEHP)	< q.l.	1

<sup>&</sup>lt; q.l. = Value below quantification limit

Cologne, 14.10.2020

Michael Stein, Dipl.-Chem. (Laboratory Manager)



## **Appendix**

### Sampling sheet



#### Sampling Sheet 55413-001 Please fill in all fields. If the fields marked\* or red outlined are not filled in, the test pieces cannot be accepted for laboratory testing. Please take one sampling sheet for each sample! The sampling instruction must be strictly maintained! Customer \* Latvijas Finieris AS Bauskas iela 59 Riga LV-1004 Testing laboratory eco-INSTITUT Germany GmbH Schanzenstr. 6-20, D-51063 Cologne Tel. +49 (0)221 - 931245-0 Fax +49 (0)221 - 931245-33 Dina Melgalve, Latvijas Finieris AS Standardisation and Certification Expert. Ph.+371 6706 59 69 X Name of manufacturer Sampler \* Name of distributor (Name, Company, (if different from customer) Sampling location \* mill Lignums, Finiera iela 6 Riga LV-1016 Product type Name of test sample/ Item \* Birch plywood Riga Ply BB/WG EXT-LN 18 mm (e.g. parquet. floor covering) Artide number n/a Batch\* S-135571 am.2 Model / programme / nme / plywood bonded with lignin-phenol-formaldehyde EXT-LN Producion date of batch \* 23.07.2020 (yyyy/mm/dd) Samples are taken 🕱 current production Sampling date storage (yyyy/mm/dd) m other before sampling packaged Storage location: Packaging material Alluminium foil, plastic film Special issues (Uncertainties, questions, possible negative effects through emissions at place of sampling - e.g. contaminations during production / storage) Validation \* Hereby the signer affirms the accuracy of the above-mentioned statements. Signature/Stamp: Date (vvvv/mm/dd): A/S "LATVIJAS FINIERIS" Quality and Production Development Department Bauskas Str. 59, Riga, Latvia, LV-1004 2020/07/24 Ding Melgalve

eco-INSTITUT Germany GmbH / Schanzenstrasse 6-20 / Carlswerk 1.19 / D-51063 Koln / Germany / Tel. +49 221.931245-0
Fax +49 221.931245-33 / eco-institut.de / eco-institut-label.de / Geschaftsfuhrer: Dr. Frank Kuebart, Daniel Tigges
HRB 17917 / USt-ID: DE 122653308 / Volksbank Rhein-Erft-Koln eG, IBAN: DE60370623651701900010, BIC: GENODED1FHH



#### Definition of terms

**V0C** 

(volatile organic compounds)

TVOC

TVOC according to DIN EN 16516:2018-01

TVOC according to AgBB/DIBt

TVOC according to eco-INSTITUT-Label

TVOC according to ISO 16000-6:2012-11

TVOC without LCI according to AgBB/DIBt and Belgian regulation

TVOC without LCI according to eco-INSTITUT-Label

CMR-VOC

(carcinogenic, mutagenic, reproduction-toxic VOC, VVOC and SVOC)

VVOC

(very volatile organic compounds)

TVVOC

TVVOC according to AgBB/DIBt and Belgian regulation

TVVOC according to eco-INSTITUT-Label SVOC (semi volatile organic compounds)

**TSVOC** 

TSVOC according to DIN EN 16516:2018-01

TSVOC without LCI according to AgBB/DIBt TSVOC without LCI according to

TSVOC with LCI according to AgBB/DIBt

SER

LCI value

eco-INSTITUT-Label

All individual compounds with a concentration  $\geq 1~\mu g/m^3$  in the retention range  $C_6$  (n-Hexane) to  $C_{16}$  (n-Hexadecane)

Total volatile organic compounds

Sum of all VOC  $\geq$  5  $\mu$ g/m<sup>3</sup> in the retention range C<sub>6</sub> to C<sub>16</sub>, calculated as toluene equivalent

Sum of all identified and calibrated VOC  $\geq$  5 µg/m³, SVOC  $\geq$  5 µg/m³ with LCI and not calibrated VOC  $\geq$  5 µg/m³ calculated as toluene equivalent

Sum of all identified and calibrated VOC  $\geq$  1 µg/m³, SVOC  $\geq$  5 µg/m³ with LCI and not calibrated VOC  $\geq$  1 µg/m³ calculated as toluene equivalent

Total area of chromatogram in the retention range  $C_6$  to  $C_{16}$ , calculated as toluene equivalent

Sum of all VOC without NIK  $\geq 5 \mu g/m^3$  in the retention range C<sub>6</sub> to C<sub>16</sub>

Sum of all VOC without NIK  $\geq 1 \mu g/m^3$  in the retention range  $C_6$  to  $C_{16}$ 

All individual substances with the following categories: Regulation (EC) No. 1272/2008: Category Car.1A and 1B, Muta. 1A and 1B, Repr. 1A and 1B TRGS 905: K1A, K1B, M1A, M1B, R1A, R1B

IARC: Group 1 and 2A

DFG (MAK lists): Category III1and III2

All individual substances with a concentration  $\geq 1~\mu g/m^3$  in the retention range  $< C_6$ 

Total very volatile organic compounds

Sum of all identified and calibrated VVOC  $\geq 5 \mu g/m^3$  with LCI

Sum of all identified and calibrated VVOC  $\geq 1 \,\mu g/m^3$  with LCI

All individual substances  $\geq 1 \mu g/m^3$  in the retention range  $C_{16}$  to  $C_{22}$ 

Total semi volatile organic compounds

Sum of all SVOC in the retention range  $C_{16}$  to  $C_{22}$ ,

calculated as toluene equivalent

Sum of all SVOC  $\geq 5 \mu g/m^3$  without LCI

Sum of all SVOC  $\geq 1 \mu g/m^3$  without LCI

Sum of all identified and calibrated SVOC  $\geq 5 \mu g/m^3$  with LCI

Specific emission rate (see "Explanation of Specific Emission Rate SER")

Lowest Concentration of Interest; calculated value for the evaluation of VOC, established by the Committee for Health-related Evaluation of Building Products (Ausschuss zur gesundheitlichen Bewertung von Bauprodukten - AgBB)



R	va	h	ı

R value according to eco-INSTITUT-Label

R value according to AgBB 2018/DIBt

R value according to Belgian regulation

R value according to AFSSET

RT (retention time)

CAS No.

(Chemical Abstracts Service)

Toluene equivalent

The quotient of the concentration and the LCI value is generated for every substance which is detected in the test chamber air. The sum of the calculated quotients results in the R value.

R value for all identified and calibrated VOC  $\geq$  1  $\mu g/m^3$  with LCI, established by the AgBB in 2018

R value for all identified and calibrated VOC  $\geq 5~\mu g/m^3$  with LCI, established by the AgBB in 2018

R value for all identified and calibrated VOC  $\geq$  5 µg/m³ with LCI, established by the Belgian regulation

R value for all identified and calibrated VOC  $\geq$  5 µg/m³ with LCI, established by ANSES (French National Agency on Food Safety, Environment, and Workplace Security)

Time for a particular analyte to pass through the system (from the column inlet to the detector)

International unique numerical identifier for a chemical substance

Concentration, calculated as toluene equivalent



#### Commentary on emission analysis

#### Test method

Measurement of the volatile organic compounds takes place in the test chamber in conditions similar to those applying in practice. Standardized test conditions are defined for the test chamber regarding loading, air exchange, relative humidity, temperature and incoming air, based on the type of test specimen and the required guideline. These conditions and the underlying standards are to be found in the section on test methods in the laboratory report.

Air samples are taken from the test chamber at defined points in time during the continuously running test. To this end, approximately 5 L of air are collected from the test chamber with an air flow rate of 100 mL/min for Tenax and approx. 100 L with an air flow rate of 0.8 L/min for DNPH (dinitrophenylhydrazine).

After thermal desorption, the substances adsorbed on Tenax are analysed using gas chromatographic separation and mass spectrometric determination. The gas chromatographic separation is performed with a slightly polar capillary column of 60 m in length.

The substances derivatized with DNPH for the determination of formaldehyde and other short-chain carbonyl compounds (C1 - C6) are analysed using high-performance liquid chromatography.

Over 200 compounds, including volatile organic compounds (C6 - C16), semi-volatile organic compounds (C16 - C22) and – insofar as possible with this method – also very volatile organic compounds (less than C6) are determined and quantified individually from  $1\mu g/m^3$ .

All other substances – insofar as is possible – are identified through comparison with a library of spectra. The quantification of these substances and non-identified substances is performed through a comparison of their signal area with the signa of the standard d8 toluene. The identification and quantification of substances is carried out, as far as technically feasible, from a concentration (evaluation limit) of  $5 \mu q/m3$  test chamber air.

#### Quality assurance

The eco-INSTITUT Germany GmbH is granted flexible scope of accreditation pursuant to DIN EN ISO/IEC 17025:2018-03. The accreditation covers the analytical determination of all volatile organic compounds, including the test chamber method.

In each analysis the analytical system is checked using an external standard based on the specifications in standard DIN EN 16516:2018-01. The stability of the analytical systems is documented based on the test standard using control charts.

Laboratory performance is assessed at least once a year in inter-laboratory comparisons by comparing the results with those obtained by other laboratories for identical samples.

A blank is run prior to introducing the test specimen into the test chamber to check for the possible presence of volatile organic compounds.

The expanded measurement uncertainty U for the analytical determination of all volatile organic compounds, including the test chamber method, is estimated to 41.7 %. The calculation is based on DIN ISO 11352:2013-03 (Nordtest).



### **Explanation of Specific Emission Rate SER**

Emission measurements are accomplished in test chambers under defined physical conditions (temperature, relative humidity, room loading, air change rate etc.).

Test chamber measurement results are directly comparable only if the investigations were accomplished under the same basic conditions.

If the differences of the physical conditions refer only to the change of air rate and/or the loading, the "SER" or "specific emission rate" can be used for comparability of the measurement results. The SER indicates how many volatile organic compounds (VOC) are released by the sample for each material unit and hour (h).

The SER can be calculated using the formula below for each proven individual component of the VOC from the data in the test report.

As material units the following are applicable:

I = unit of length (m) relation between emission and length
a = unit area (m²) relation between emission and surface
v = unit volume (m³) relation between emission and volume
u = piece unit (unit = piece) relation between emission and complete unit

From this the different dimensions for SER result:

 $\begin{array}{lll} length\text{-specific} & SER_l & in \ \mu g/(m\cdot h) \\ surface\text{-specific} & SER_a & in \ \mu g/(m^2\cdot h) \\ volume\text{-specific} & SER_v & in \ \mu g/(m^3\cdot h) \\ unit specific & SER_u & in \ \mu g/(u\cdot h) \end{array}$ 

SER thus represents a product specific rate, which describes the mass of the volatile organic compound, which is emitted by the product per time unit at a certain time after beginning of the examination.

- q specific air flow rate (quotient from change of air rate and loading)
- c concentration of the measured substance(s)

The result can be indicated in milligrams (mg) in place of micro grams ( $\mu$ g), whereby 1 mg = 1000  $\mu$ g.