

PERMISSIBLE WORKING PRESSURE - POTABLE WATER

Fluid transported: water acc. to DIN 2000

Temperature	Years of service	aquatherm green pipe SDR 11 S	aquatherm green pipe SDR 7,4 S	aquatherm green pipe SDR 6 S	aquatherm green pipe SDR 7,4 MS	aquatherm green pipe SDR 7,4 MF	aquatherm green pipe SDR 9 MF RP			
		Permissible working pressure in bar and (psi)								
		bar	(psi)	bar	(psi)	bar	(psi)	bar	(psi)	
20 °C 68 °F	1	15,0	(218)	23,8	(345)	30,0	(435)	28,6	(415)	
	5	14,1	(205)	22,3	(323)	28,1	(408)	26,8	(389)	
	10	13,7	(199)	21,7	(315)	27,3	(396)	26,1	(379)	
	25	13,3	(193)	21,1	(306)	26,5	(384)	25,3	(367)	
	50	12,9	(187)	20,4	(296)	25,7	(373)	24,5	(355)	
30 °C 86 °F	1	12,8	(186)	20,2	(293)	25,5	(370)	24,3	(352)	
	5	12,0	(174)	19,0	(276)	23,9	(347)	22,8	(331)	
	10	11,6	(168)	18,3	(265)	23,1	(335)	22,0	(319)	
	25	11,2	(162)	17,7	(257)	22,3	(323)	21,3	(309)	
	50	10,9	(158)	17,3	(251)	21,8	(316)	20,7	(300)	
Potable water (cold) Potable water (warm)	40 °C 104 °F	1	17,1	(248)	21,5	(312)	20,5	(297)	18,7	(271)
		5	16,0	(232)	20,2	(293)	19,2	(278)	18,0	(261)
		10	15,6	(226)	19,6	(284)	18,7	(271)	17,7	(257)
		25	15,0	(218)	18,8	(273)	18,0	(261)	17,4	(252)
		50	14,5	(210)	18,3	(265)	17,5	(254)	17,0	(247)
	50 °C 122 °F	1	14,5	(210)	18,3	(265)	17,5	(254)	15,9	(231)
		5	13,5	(196)	17,0	(247)	16,2	(235)	15,3	(222)
		10	13,1	(190)	16,5	(239)	15,7	(228)	15,1	(219)
		25	12,6	(183)	15,9	(231)	15,2	(220)	14,8	(215)
		50	12,2	(177)	15,4	(223)	14,7	(213)	14,5	(210)
	60 °C 140 °F	1	12,2	(177)	15,4	(223)	14,7	(213)	13,5	(196)
		5	11,4	(165)	14,3	(207)	13,7	(199)	13,0	(189)
		10	11,0	(160)	13,8	(200)	13,2	(191)	12,8	(186)
		25	10,5	(152)	13,3	(193)	12,6	(183)	12,5	(181)
		50	10,1	(146)	12,7	(184)	12,1	(175)	12,3	(178)
	65 °C 149 °F	1	11,6	(168)	14,6	(212)	13,9	(202)	12,4	(180)
		5	10,8	(157)	13,6	(197)	12,9	(187)	11,9	(173)
		10	10,4	(151)	13,1	(190)	12,5	(181)	11,7	(170)
		25	10,0	(145)	12,6	(183)	12,0	(174)	11,4	(165)
		50	8,8	(128)	11,1	(161)	10,6	(154)	11,2	(162)
	70 °C 158 °F	1	10,3	(149)	13,0	(189)	12,4	(180)	11,4	(165)
		5	9,5	(138)	11,9	(173)	11,4	(165)	10,9	(158)
		10	9,3	(135)	11,7	(170)	11,1	(161)	10,7	(155)
		25	8,0	(116)	10,1	(146)	9,6	(139)	10,5	(152)
		30	7,0	(102)	8,8	(128)	9,3	(135)	10,3	(149)
		50	6,7	(97)	8,5	(123)	8,1	(117)	10,2	(148)

Faser and Stabi composite pipe: high working stress at lower wall thickness and higher flow rate

SDR = Standard Dimension Ratio (diameter/wall thickness ratio)

S = single layer

MS = multilayer stabi - integrated aluminium-layer

MF = multilayer faser

MF RP = multilayer faser - raised pressure (resistance)

The determination of the allowable pressures resulted from the specific conditions to which pipe system components in the drinking water domestic installation are exposed to. Limiting factors such as increased flow rates, the use of disinfectants, increased content of oxygen, etc. were considered by the use of the appropriate safety factors. For fittings of butt-welded pipe segments a reduction factor of 0.75 (reduction of the table values by 25%) is effective.

PERMISSIBLE WORKING PRESSURE

for general pressure pipe applications in permanent operation

charted application ranges on page 23 and 24

Temperature	Years of service	aquatherm blue pipe SDR 17,6 MF		aquatherm blue pipe SDR 11 MF & MF OT aquatherm lilac pipe SDR 11 S		aquatherm green pipe SDR 7,4 MF		aquatherm green pipe SDR 9 MF RP	
		Permissible working pressure in bar and (psi)							
		bar	(psi)	bar	(psi)	bar	(psi)	bar	(psi)
10 °C 50 °F	1	12,8	(186)	27,8	(403)	30,2	(438)	28,8	(418)
	5	12,0	(174)	26,2	(380)	28,2	(409)	27,9	(405)
	10	11,7	(170)	25,6	(371)	27,7	(402)	27,5	(399)
	25	11,4	(165)	24,7	(358)	26,9	(390)	27,1	(393)
	50	11,1	(161)	24,1	(350)	26,1	(379)	26,7	(387)
	100	10,8	(157)	23,5	(341)	25,2	(366)	26,3	(381)
15 °C 59 °F	1	11,8	(171)	25,7	(373)	29,4	(426)	26,9	(390)
	5	11,1	(161)	24,2	(351)	27,4	(397)	26,0	(377)
	10	10,8	(157)	23,6	(342)	26,9	(390)	25,7	(373)
	25	10,5	(152)	22,8	(331)	26,1	(379)	25,2	(366)
	50	10,2	(148)	22,2	(322)	25,3	(367)	24,9	(361)
	100	9,9	(144)	21,6	(313)	24,5	(355)	24,5	(355)
20 °C 68 °F	1	10,9	(158)	23,8	(345)	28,6	(415)	25,0	(363)
	5	10,3	(149)	22,3	(323)	26,8	(389)	24,2	(351)
	10	10,0	(145)	21,7	(315)	26,1	(379)	23,9	(347)
	25	9,6	(139)	21,0	(305)	25,3	(367)	23,5	(341)
	50	9,4	(136)	20,4	(296)	24,5	(355)	23,1	(335)
	100	9,1	(132)	19,9	(289)	23,7	(344)	22,8	(331)
30 °C 86 °F	1	9,3	(135)	20,2	(293)	24,3	(352)	21,7	(315)
	5	8,7	(126)	18,9	(274)	22,8	(331)	20,9	(303)
	10	8,5	(123)	18,4	(267)	22,0	(319)	20,6	(299)
	25	8,2	(119)	17,8	(258)	21,3	(309)	20,2	(293)
	50	7,9	(115)	17,3	(251)	20,7	(300)	19,9	(289)
	100	7,7	(112)	16,8	(244)	20,0	(290)	19,7	(286)
40 °C 104 °F	1	7,9	(115)	17,1	(248)	20,5	(297)	18,6	(270)
	5	7,4	(107)	16,0	(232)	19,2	(278)	18,0	(261)
	10	7,2	(104)	15,6	(226)	18,7	(271)	17,7	(257)
	25	6,9	(100)	15,0	(218)	18,0	(261)	17,3	(251)
	50	6,7	(97)	14,6	(212)	17,5	(254)	17,1	(248)
	100	6,5	(94)	14,1	(205)	16,8	(244)	16,8	(244)
50 °C 122 °F	1	6,7	(97)	14,5	(210)	17,5	(254)	15,9	(231)
	5	6,2	(90)	13,5	(196)	16,2	(235)	15,3	(222)
	10	6,0	(87)	13,1	(190)	15,7	(228)	15,1	(219)
	25	5,8	(84)	12,6	(183)	15,2	(220)	14,7	(213)
	50	5,6	(81)	12,2	(177)	14,7	(213)	14,5	(210)
	100	5,5	(80)	11,9	(173)	14,1	(205)	14,3	(207)
60 °C 140 °F	1	5,6	(81)	12,2	(177)	14,7	(213)	13,5	(196)
	5	5,2	(75)	11,4	(165)	13,7	(199)	13,0	(189)
	10	5,1	(74)	11,0	(160)	13,2	(191)	12,7	(184)
	25	4,9	(71)	10,6	(154)	12,6	(183)	12,4	(180)
	50	4,7	(68)	10,3	(149)	12,1	(175)	12,2	(177)
	100	4,7	(68)	10,3	(149)	12,4	(180)	11,3	(164)
70 °C 158 °F	5	4,4	(64)	9,6	(139)	11,4	(165)	10,9	(158)
	10	4,2	(61)	9,2	(133)	11,1	(161)	10,7	(155)
	25	3,7	(54)	8,0	(116)	9,6	(139)	10,4	(151)
	50	3,1	(45)	6,8	(99)	8,1	(117)	10,2	(148)
	100	3,1	(45)	6,8	(99)	8,1	(117)	10,2	(148)
	1	4,3	(62)	9,4	(136)	11,7	(170)	10,4	(151)
75 °C 167 °F	5	4,0	(58)	8,7	(126)	10,8	(157)	9,9	(144)
	10	3,7	(54)	8,0	(116)	10,0	(145)	9,7	(141)
	25	3,0	(44)	6,4	(93)	8,0	(116)	9,5	(138)
	50	2,5	(36)	5,4	(78)	6,7	(97)	9,3	(135)
	100	2,4	(35)	5,2	(75)	6,2	(90)	8,6	(125)
	1	4,0	(58)	8,6	(125)	10,4	(151)	9,5	(138)
80 °C 176 °F	5	3,5	(51)	7,7	(112)	9,2	(133)	9,0	(131)
	10	3,0	(44)	6,5	(94)	7,8	(113)	8,9	(129)
	25	2,4	(35)	5,2	(75)	6,2	(90)	8,6	(125)
	100	2,0	(29)	4,3	(62)	5,1	(74)	7,3	(106)

SDR = Standard Dimension Ratio (diameter/wall thickness ratio)

S = single layer

MS = multilayer stabi - integrated aluminium-layer

MF = multilayer faser

MF RP = multilayer faser - raised pressure (resistance)

For fittings of butt-welded pipe segments a reduction factor of 0.75 (reduction of the table values by 25%) is effective.