

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Braeside Mills Operations P/L, T/A as Armstrong Flooring
29-39 Mills Road
Braeside VIC 3195

Test Number : 23-001326
Issue Date : 19/05/2023
Print Date : 15/06/2023
Order Number : 201807

Sample Description Clients Ref : "Armstrong Flooring Luxury Vinyl 2.0mm"
Vinyl flooring
Colour : Timber look
End Use : Flooring
Nominal Composition : Multi layered filled PVC
Nominal Thickness : 2mm



296886

63885

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



A blue ink signature of Fiona McDonald.

Fiona McDonald

APPROVED SIGNATORY

A blue ink signature of Michael A. Jackson.

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Braeside Mills Operations P/L, T/A as Armstrong Flooring
29-39 Mills Road
Braeside VIC 3195

Test Number : 23-001326
Issue Date : 19/05/2023
Print Date : 15/06/2023
Order Number : 201807

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 05-04-2023

Date Tested 19-05-2023

CHF Value	1	2	3	Mean
Length	≥11.0	-	-	- kW/m²
Width	≥11.0	10.6	≥11.0	10.6 kW/m²

Smoke Value	1	2	3	Mean
Length	36	-	-	- %.min
Width	47	46	38	44 %.min

Observations:

Melting	Yes
Blistering	Yes

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using Roberts 656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

296886

63885

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

